

Product data sheet, September 2015

Makrolon® multi UV 5M/40-20

Multiwall polycarbonate sheet



Your benefits:

- extremely heat-insulating
- high rigidity
- good load bearing capacity



Makrolon® multi UV 5M/40-20 is a polycarbonate sheet of 40 mm thickness, with a M-structure for enhanced stiffness. It combines good load bearing properties, excellent thermal insulation, light transmission and excellent weather resistance. The sheet is lightweight, impact resistant and easy to install.

Makrolon® multi UV 5M/40-20 is ideal for flat glazing applications.

- conservatories
- industrial glazing, sports halls
- partition walls
- skylights, northlight glazing
- roofing, cladding (facades)

The sheets are produced with a coextruded UV-protective layer, which is homogeneously fused with the sheet material. This UV-protected side must be installed facing upwards/outwards. It provides **Makrolon® multi UV** with a highly effective protection against weathering, guaranteed for 10 years.

On request:


IQ-Relax

Makrolon® multi IQ-Relax are opal white sheets, which dramatically reduce the heat of the sunlight, allowing the visible light to pass through. More light, less heat!

| TECH | NICAL DATA | A (TYPICAL VALU | IES) | | | | |
|---|---------------|---|--|--|--|--|--|
| Area weight | | 4.2 kg/m² | | | | | |
| Sheet width | | 980, 1,200, and 1 | 980, 1,200, and 1,230 mm | | | | |
| Possible delivery lengths | | 2,000 to 6,000 mi | 2,000 to 6,000 mm | | | | |
| Light transmittance τ _{D65} (UV-absorbing) | | clear 1099: white 1146: IQ-Relax: bronze 1845: | approx. 47 % approx. 35 % approx. 27 % approx. 10 % | | | | |
| Total energy transmission | g | clear 1099: white 1146: IQ-Relax: bronze 1845: | approx. 47 % approx. 38 % approx. 30 % approx. 28 % | | | | |
| Heat transfer coefficient Ug (2) | | | 1.1 W/m² K (vertical application) 1.1 W/m² K (horizontal application) | | | | |
| Coefficient of thermal expa | ansion $lpha$ | 0.065 mm/m °C | 0.065 mm/m °C | | | | |
| Possible expansion due to heat and moisture | | 3 mm/m | 3 mm/m | | | | |
| Max. service temperature without load | | 120°C | 120°C | | | | |
| Weighted sound reduction | ı index | 19 dB | | | | | |
| Fire rating (1) • Europe w | hite 1146 | B-s2, d0 | B-s2, d0 (EN13501-1) | | | | |

⁽¹⁾ Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased Polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards, except for Product rated "B1" in accordance with DIN 4102.

⁽²⁾ Heat transfer coefficient Ug according to EN ISO 10077-2





Makrolon® multi UV 5M/40-20

Multiwall polycarbonate sheet



Ideas, innovative, intelligent, interesting... Covestro i-line represents the next generation of quality products. This seal guarantees innovative and intelligent first-class solutions at all times for a multitude of requirements.

If **Makrolon® multi UV 5M/40-20** is used in applications of roofing or walling, the forces applied by wind and snow loads must be absorbed by a suitable sub-structure. We recommend taking the support distance for each load from the diagram.

The diagram shows the load bearing capacity for **Makrolon® multi UV 5M/40-20** (supported on all sides, rebate depth ≥20 mm). If the rebate depth is smaller, the support distances should be reduced suitably for the given load. For pure wind loads the loads may be increased by a factor of 1.1.

If sufficiently stable profiles are used, the load increases by a factor of 1.2. You can find further sheet widths and statements on barrel yaults in the Technical Manual.

Load bearing characteristics (determination):


The system resistance (boundary state of load bearing capacity) of Makrolon® multi UV 5M/40-20 was determined in accordance with European guideline ETAG 10 (European Technical Approval on "self-supporting light-transmitting roofing systems", which came into force in September 2002) in real tests. The characteristic values of system resistance were determined in an unfavorable system, i.e. the sheets were not fixed, but laid loosely. The loads are applied as uniformly distributed linear loads, i.e. load components acting vertically on the sheet, e.g. snow.


sive tests on real systems carried out by the KPF in Erkelenz/Germany (testing, monitoring and certification centre recognized by the building inspectorate). Adequate safety values, which should be assessed on a case-by-case basis, are to be observed with regard to these values.

These values are guide values, which were determined in exten-

In general, experience has shown that a safety factor of 1.3 is adequate with regard to the measured resistance values. This safety factor is included in the load table and the diagram.

These statements do not replace the specified national certificates, e.g. building inspectorate approval (Bauaufsichtliche Zulassung Germany), Avis Techniques (France), etc.





| Load | kN/m² | 0.5 | 0.75 | 1.0 | 1.5 | 2.0 | 3.0 | Width in mm |
|-------------------|-------|-----|------|-----|-----|-----|-----|-----------------|
| Length or support | m | ∞ | ∞ | 4.5 | 3.3 | 2.6 | 2.0 | 980 |
| spacing A | m | ∞ | 4.5 | 3.8 | 3.0 | 2.5 | 1.8 | 1,200 and 1,230 |

Covestro also produces solid sheets in polycarbonate (Makrolon® GP) and in polyester (Vivak® and Axpet®). For more information, take a look at www.sheets.covestro.com.



Covestro Deutschland AG Business Unit Polycarbonates 51365 Leverkusen Germany

www.sheets.covestro.com sales.sheetsEMEA@covestro.com The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations, including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoints. Such testing has not necessarily been done by Covestro. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or commendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to a ny material or its use. No license is implied or in fact granted under the claims of any patent.